

Composizione Chimica valida sia per lingotti che per fusioni.  
 Chemical Composition acceptable both for ingots and for castings.

### 6.3 Accepted Alloys

#### 6.3.1

Notation	Product groups
CC499K (CuSn5Zn5Pb2-C)	B and C

Constituents (% (m/m)):

Cu	Sn	Zn	Pb	Ni
84,0% - 88,0%	4,0% - 6,0%	4,0% - 6,0%	0,2% - 3,0%	0,1% - 0,60%

Impurities (% (m/m)):

Fe	P	S	Sb
≤ 0,30%	≤ 0,04%	≤ 0,04%	≤ 0,10%

*Each other impurity < 0,02%*

#### Basis for acceptance

German Co-normative Research Report RG\_CPDW\_01\_074  
 Dossier John Nuttall (March 2006)