

Composizione Chimica valida sia per lingotti che per fusioni.
 Chemical Composition acceptable both for ingots and for castings.

5.3 Accepted Alloys

5.3.1

Notation	Product groups
CC770S (CuZn36Pb-C)	B and C

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al
62,0% - 64,0%	Remainder	0,2% - 1,6%	0,04% - 0,14%	0,5% - 0,7%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0,3%	≤ 0,1%	≤ 0,2%	≤ 0,3%

Each other impurity < 0,02%

Basis for acceptance

UBA opinion (29 Jan 2014)